UPUTA ZA UPOTREBU
CRNO-BIJELIH »EFKE KB« (35 mm) I R (smotanih) NEGATIV FILMOVA

»EFKE KB 14« 35-milimetarski film »EFKE R 14« smotani film ortopankromatski 14 DIN = 20 ASA	ekstremno sitnozrnasti tankoslojni vrlo velika konturna oštrina
»EFKE KB 17« 35-milimetarski film »EFKE R 17« smotani film ortopankromatski 17 DIN = 40 ASA	izrazito sitnozrnasti tankoslojni srednja osjetljivost velika konturna oštrina
»EFKE KB 21« 35-milimetarski film »EFKE R 21« smotani film pankromatski 21 DIN = 100 ASA	sitnozrnasti tankoslojni visoka osjetljivost dobra konturna oštrina

Ulaganje filmova: pri prigušenom svjetlu.
Podrobni tehnički podaci o svojstvima i opremi KB i R negativ filmova navedeni su u »Fotokemika« tehničkim uputama FP N4, N5, N6 0571.
Osvjetljavanje ovisi o uvjetima razvijanja.
Za razvijanje u razvijačima što se dolje navode preporučuju se ove vrijednosti za podešavanje svjetlomjera:

Negativ filmovi	Razvijači i trajanje razvijanja	Dnevna rasvjeta	Umjetna rasvj. Wolframova el. žarulja
		svjetlomjer podesiti na	
KB 14 R 14	FR 5 6 minuta, 20°C	17 DIN = 40 ASA	14 DIN = 20 ASA
	FR E24 11 minuta, 20°C	21 DIN = 100 ASA	18 DIN = 50 ASA
KB 17 R 17	FR 5 7 minuta, 20°C	20 DIN = 80 ASA	17 DIN = 40 ASA
	FR E24 15 minuta, 20°C	23 DIN = 160 ASA	21 DIN = 100 ASA
KB 21 R 21	FR 5 8 minuta, 20°C	23 DIN = 160 ASA	21 DIN = 100 ASA
	FR E24 18 minuta, 20°C	25 DIN = 250 ASA	23 DIN = 160 ASA

Obrađuje se u potpunom mraku.
Fiksiranje: Preporučuje se kiseli fiksir FF 1 (pri 18 — 20°C), uz povremeno miješanje.
Ispiranje: Ispire se tekućom vodom temperature 15 — 25°C 30 minuta.
Upozorenje! U slučaju tvorničke pogreške odobrit će se zamjena odgovarajuće količine reklamiranog filma. Nikakvi se drugi zahtjevi za naknadom neće priznati.
Uz reklamirani materijal treba navesti broj proizvodnje.
Po licenciji »Du Pont Fotowerke« »ADOX« — filmove proizvodi »Fotokemika«, Zagreb.

FU 1 0474

»FOTOKEMIKA«
TVORNICA FILMOVA I FOTO-PAPIRA
ZAGREB — JUGOSLAVIJA

BLACK & WHITE NEGATIVE FILMS EFKE KB (35 mm) AND R (roll) INSTRUCTIONS FOR USE

EFKE KB 14 35 mm film EFKE R 14 roll film Orthopanchromatic 14 DIN = 20 ASA	Extremely fine grain Thin layer Very high contour sharpness
EFKE KB 17 35 mm film EFKE R 17 roll film Orthopanchromatic 17 DIN = 40 ASA	Distinctly fine grain Thin layer Medium speed High contour sharpness
EFKE KB 21 35 mm film EFKE R 21 roll film Panchromatic 21 DIN = 100 ASA	Fine grain Thin layer High speed Good contour sharpness

Loading and unloading of the camera: in subdued light.
Detailed technical data on properties and packing of KB and R negative films are quoted in Fotokemika Technical instruction FP N4, N5, N6 0571
Exposure depends on developing conditions.
For developing in developers listed below, the following walues for exposure meter adjustment are recommended:

Films	Developers and developing time	Daylight	Incandescent lamp Artificial light
		adjust exposure meter to	
KB 14 R 14	FR 5 6 minutes. 20°C	17 DIN = 40 ASA	14 DIN = 20 ASA
	FR E24 11 minutes, 20°C	21 DIN = 100 ASA	18 DIN = 50 ASA
KB 17 R 17	FR 5 7 minutes, 20°C	20 DIN = 80 ASA	17 DIN = 40 ASA
	FR E24 15 minutes, 20°C	23 DIN = 160 ASA	21 DIN = 100 ASA
KB 21 R 21	FR 5 8 minutes, 20°C	23 DIN = 160 ASA	21 DIN = 100 ASA
	FR E24 18 minutes, 20°C	25 DIN = 250 ASA	23 DIN = 160 ASA

These films are processed in total darkness.
Fixing — We recommend acid fixer FF 1 (at 18 — 20°C) with intermittent stirring.
Washing — In tap water of 15 — 25°C for about 30 minutes.
NOTE! — This product will be replaced if defective in manufacture. Except for such replacement, no other claim will be accepted.
The claim should quote the production number (year of manufacture).
Manufactured by Fotokemika — Zagreb, Yugoslavia under the licence of Du Pont Fotowerke ADOX.

FU 1 0474

F O T O K E M I K A
FILMS AND PHOTOGRAPHIC PAPERS FACTORY
ZAGREB — YUGOSLAVIA